

Company: Chongqing Titanium
TABLE C-1 The goods exported to Australia

Item No.	Product code	MCC Category - Production Process	MCC	Product specifications / typical properties								
				Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	R-298	sulfate process	S	R-298	general use	91	Alumina, Zirconia	Present	2.5	≤20	/	R2
2	R-248	sulfate process	S	R-248	plastic	95	Alumina, Zirconia	Present	2.5	≤19	/	R2
3	R-249	sulfate process	S	R-249	plastic specialized	96	Alumina	Present	2.5	≤17	/	R2

Company: Chongqing Titanium
TABLE C-2 Like goods sold on the domestic market

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	R-298	sulfate process	S	R-298	general use	91	Alumina, Zirconia	Present	2.5	≤20	/	R2
2	R-248	sulfate process	S	R-248	plastic	95	Alumina, Zirconia	Present	2.5	≤19	/	R2
3	R-249	sulfate process	S	R-249	plastic specialized	96	Alumina	Present	2.5	≤17	/	R2
4	R-228	sulfate process	S	R-228	inks	91	Alumina	Present	2.5	≤18	/	R2

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	R-298	sulfate process	S	R-298	general use	91	Alumina, Zirconia	Present	2.5	≤20	/	R2
2	R-248	sulfate process	S	R-248	plastic	95	Alumina, Zirconia	Present	2.5	≤19	/	R2
3	R-249	sulfate process	S	R-249	plastic specialized	96	Alumina	Present	2.5	≤17	/	R2
4	R-228	sulfate process	S	R-228	inks	91	Alumina	Present	2.5	≤18	/	R2
5	R-288	sulfate process	S	R-288	Waterborne	90	silica, Alumina	Present	2.5	≤22	/	R2