

LB Group Co., Ltd.

TABLE C-1 The goods exported to Australia

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	BLR-698	sulfate process	S	BLR-698	for coatings and ink	94	Alumina, Zirconia	Present	1.2	17	4.1	R2
2	BLR-699	sulfate process	S	BLR-699	for coatings and ink	95	Alumina, Zirconia	Present	1.1	18	4.1	R2
3	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2
4	TR52	sulfate process	S	TR52	for coatings and ink	95	Alumina	Present	1.3	14	4.1	R2

LB Group Co., Ltd.

TABLE C-2 Like goods sold on the domestic market

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	BLR-500	sulfate process	S	BLR-500	general use	98.5	None	Not Present	/	/	4.2	R1
2	BLR-501	sulfate process	S	BLR-501	general use	98.5	None	Not Present	1	15	4.2	R1
3	BLR-631	sulfate process	S	BLR-631	for coatings and ink	95	Alumina	Present	1.3	14	4.1	R2
4	BLR-698	sulfate process	S	BLR-698	for coatings and ink	94	Alumina, Zirconia	Present	1.2	17	4.1	R2
5	BLR-698+	sulfate process	S	BLR-698+	for coatings and ink	94	Alumina, Zirconia	Present	1.2	17	4.1	R2
6	BLR-699	sulfate process	S	BLR-699	for coatings and ink	95	Alumina, Zirconia	Present	1.1	18	4.1	R2
7	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2
8	TR28	sulfate process	S	TR28	for plastics	98	Alumina	Present	/	12	4.1	R1
9	TR52	sulfate process	S	TR52	for coatings and ink	95	Alumina	Present	1.3	14	4.1	R2
10	TR53	sulfate process	S	TR53	for ink	88	Alumina, Silica	Present	1.2	22	3.9	R3

Note: LB Group does not produce TR28. The product was purchased from outside company

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2
2	BLR-698	sulfate process	S	BLR-698	for coatings and	94	Alumina, Zirconia	Present	1.2	17	4.1	R2
3	BLR-699	sulfate process	S	BLR-699	for coatings and	95	Alumina, Zirconia	Present	1.1	18	4.1	R2
4	TR52	sulfate process	S	TR52	for coatings and	95	Alumina	Present	1.3	14	4.1	R2
5	TR53	sulfate process	S	TR53	for ink	88	Alumina, Silica	Present	1.2	22	3.9	R3
6	BLR-501	sulfate process	S	BLR-501	general use	98.5	None	Not Present	1	15	4.2	R1
7	BLR-500	sulfate process	S	BLR-500	general use	98.5	None	Not Present	/	/	4.2	R1
8	BLR-631	sulfate process	S	BLR-631	for coatings and	95	Alumina	Present	1.3	14	4.1	R2
9	BLR-698+	sulfate process	S	BLR-698+	for coatings and	94	Alumina, Zirconia	Present	1.2	17	4.1	R2
10	TR28	sulfate process	S	TR28	for plastics	98	Alumina	Present	/	12	4.1	R1

Note: LB Group does not produce TR28. The product was purchased from outside company