

LB Sichuan Titanium Industry Co., Ltd.
TABLE C-1 The goods exported to Australia

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	LR-108	sulfate process	S	LR-108	for plastics	98	Alumina	Present	1.1	15	4.1	R1
2	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2

LB Sichuan Titanium Industry Co., Ltd.

TABLE C-2 Like goods sold on the domestic market

				Product specifications / typical properties								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	LR-108	sulfate process	S	LR-108	for plastics	98	Alumina	Present	1.1	15	4.1	R1
2	LR-961	sulfate process	S	LR-961	for coatings	95	Alumina	Present	1	18	4.1	R2
3	LR-972	sulfate process	S	LR-972	coatings and plas	93	Alumina, Silica	Present	1.2	19	4.1	R2
4	LR-982	sulfate process	S	LR-982	atings, inks and p	95	Alumina	Present	1	17	4.1	R2
5	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2

TABLE C-3 MCC

				Product specifications / typical properties\								
Item No.	Product code	MCC Category - Production Process	MCC	Product code or grade used to market product (if different to internal product code)	Recommended applications	Titanium dioxide minimum content (%), dry weight basis	Inorganic surface treatment or coating (please identify e.g. alumina, zirconia, silica etc)	Organic surface treatment or coating (yes or no)	Bulk density (g/cm3)	Oil absorption (g/100 g)	Specific gravity (g/cm3)	ISO 591-1:2000 classification - Type / grade (e.g. R2)
1	R-996	sulfate process	S	R-996	for coatings	95	Alumina, Zirconia	Present	1.2	18	4.1	R2
2	LR-972	sulfate process	S	LR-972	for coatings and plastics	93	Alumina, Silica	Present	1.2	19	4.1	R2
3	LR-961	sulfate process	S	LR-961	for coatings	95	Alumina	Present	1.0	18	4.1	R2
4	LR-982	sulfate process	S	LR-982	for coatings, inks and pl	95	Alumina	Present	1	17	4.1	R2
5	LR-108	sulfate process	S	LR-108	for plastics	98	Alumina	Present	1.1	15	4.1	R1